

Products description

Metallic polyurethane material for heat transfer applications.

Thickness : 60 microns (USA : 2,4 mil).

Carrier : self-adhesive and transparent polyester.

Norm : references 420 – 421 : Oekotex label standard 100 class II.

Suitable for

HOTMARK Metallic: Cotton, polyester, acrylic and similar fibres.

Application advises

- 1) Cut the material in reverse with a flex blade.
- 2) Weed the excess material.
- 3) Heat press the image on the garment with its polyester carrier protected by a silicone paper at 140°C (USA: 280°F) – 10-15 seconds – medium pressure.
- 4) Peel the carrier off when cold.

Maintenance

Always respect the instructions mentioned on garments.
After heat pressing, wait 24 hours before the first wash.

Washing : Hand washing only - without bleach or any aggressive washing products.

Tumble-drying : no

Dried cleaning : no

Ironing : backside

Storage of the roll : vertically, one year in a dry room, 15-30°C (USA : 60-85°F), protected from sunlight.

Caution

Be careful with the metallic quality: Never heat-press this product twice.
Those recommendations are based on our own experiences.
We always recommend making trials before starting standard production.

April 2012



8 rue Auguste Poncetton BP 30164
42004 St Etienne cedex 1 (FRANCE)
Tel. +33 (0)4 77 49 20 90
Fax +33 (0)4 77 25 79 82
info@chemica.fr
www.chemica.fr



3495 Piedmont road Bldg.11, suite 710
ATLANTA, GA 30305 (USA)
Tel. +1 4074 495 5991
Fax +1 404 233 8625
rosa.lopes@chemica.fr
www.chemica.fr



RM 2207-9 Tower two lippo ctr
89 Queensway Admiralty HONK KONG
Cell. +33 (0)6 34 51 25 58
Tel. +33 (0)4 77 49 20 97
info@chemica.fr
www.chemica.fr