

### Product description

Metal coated aspect polyurethane media for use on eco and true solvent printers for heat transfer applications.

**Thickness** : 85 microns (USA : 3,3 mil).

**Carrier** : white paper.

### Suitable for

Cotton, polyester, acrylic and similar fibres.

### Application advises

#### **1) printing and cutting**

- Prepare the image on positive following the instruction of the printer manufacturer:
  - Take care of the printing (45°C – USA: 110°F) and drying temperatures (50°C – USA: 120°F).
  - Use the adequate printing profile (for instance, with Roland, select Colorip or Versawork, and then profile TTRH, textile).
- Remove the flex from the printer and wait for the complete drying of inks at room temperature, at least 4 hours.

#### **2) heat pressing**

- Weed the excess material.
- Using an application tape is not compulsory to transfer the image. It is possible to transfer the image by hand or with a polyester application tape.
- Position and heat press the image on the garment protected by a silicone paper at 140°C (USA: 280°F) – 20 seconds – medium pressure.
- If you use it, peel the application tape off when cold.

### Maintenance

Always respect the instructions mentioned on garments. After heat pressing, wait 24 hours before the first wash.

**Washing** : Delicate product: cold washing only - without bleach or any aggressive washing products.

**Tumble drying** : no

**Dried cleaning** : no

**Ironing** : backside

**Storage of the roll** : vertically, one year in a dry room, 15-25°C (USA : 60-80°F), protected from sunlight.

### Caution

Printable media are very sensitive: always handle with care, with clean hands.

Always store the roll in a plastic bag protected from dust.

It is important always using official inks from the printer producer.

Those recommendations are based on our own experiences.

We always recommend making trials before starting standard production.

March 2011

#### **CHEMICA**

8 rue Auguste Poncetton  
42000 Saint-Etienne – France  
Tel : +33.(0)4.77.49.20.90  
Fax : +33.(0)4.77.25.79.82  
[info@chemica.fr](mailto:info@chemica.fr) - [www.chemica.fr](http://www.chemica.fr)

#### **CHEMICA US**

3495 Piedmont Road – Bldg 11, Suite 710  
Atlanta, GA 30305 – USA  
Tel : +1 404.495.5991 – cell +1.404.754.0548  
Fax : +1.404.233.8625  
[rosa.lopes@chemica.fr](mailto:rosa.lopes@chemica.fr) – [www.chemica.fr](http://www.chemica.fr)