

### Product description

Polyurethane media with glitters for use on eco and true solvent printers for heat transfer applications.

**Thickness:** 220 microns (USA : 8,6 mil) for white ref. 1720 - 140 microns (USA : 5,5 mil) for silver ref. 1721

**Carrier :** Transparent polyester.

### Suitable for

Cotton, polyester, acrylic and similar fibres.

### Application advises

#### 1) printing and cutting

- Prepare the image on positive following the instruction of the printer producer :
  - Take care of the printing (45°C – USA : 110°F) and drying temperatures (50°C – USA : 120°F).
  - Use the adequate printing profile (for instance, with Roland, select Colorip or Versawork, and then profile TTRH, textile).
- Remove the flex from the printer and wait for the complete drying of inks at room temperature, at least 4 hours.

#### 2) heat pressing

- Weed the excess material.
- Using an application tape is not compulsory to transfer the image. It is possible to transfer the image by hand or with a strong tack polyester application tape.
- Position and heat press the image on the garment protected by a silicone paper at :
  - 160°C (USA : 320°F) for silver ref. 1721
  - 180°C (USA : 360°F) for white ref. 1720during 20 seconds – medium pressure.
- If you use it, peel the application tape off when warm.

### Maintenance

Always respect the instructions mentioned on garments. After heat pressing, wait 24 hours before the first wash.

**Washing :** 40°C (USA : 100°F) max. inside out - without bleach or any aggressive washing products.

**Tumble-drying :** yes

**Dried cleaning :** no

**Ironing :** backside

**Storage of the roll :** vertically, one year in a dry room, 15-25°C (USA : 60-80°F), protected from sunlight.

### Caution

Printable media are very sensitive : always handle with care, with clean hands.

Always store the roll in a plastic bag protected from dust.

It is important always using official inks from the printer producer.

Those recommendations are based on our own experiences.

We always recommend making trials before starting standard production.

February 2011

#### **CHEMICA**

8 rue Auguste Poncetton  
42000 Saint-Etienne – France  
Tel : +33.(0)4.77.49.20.90  
Fax : +33.(0)4.77.25.79.82  
[info@chemica.fr](mailto:info@chemica.fr) - [www.chemica.fr](http://www.chemica.fr)

#### **CHEMICA US**

3495 Piedmont Road – Bldg 11, Suite 710  
Atlanta, GA 30305 – USA  
Tel : +1 404.495.5991 – cell +1.404.754.0548  
Fax : +1.404.233.8625  
[rosa.lopes@chemica.fr](mailto:rosa.lopes@chemica.fr) – [www.chemica.fr](http://www.chemica.fr)